



Europäisches Patentamt
European Patent Office
Office européen des brevets

(11) Publication number:

**0 262 891
A3**

(12)

EUROPEAN PATENT APPLICATION

(21) Application number: 87308550.0

(51) Int. Cl.4: **C08L 63/00 , //C08J3/00,
(C08L63/00,101:00)**

(22) Date of filing: 28.09.87

(30) Priority: 30.09.86 JP 232964/86
11.03.87 JP 54180/87
11.03.87 JP 54181/87

(43) Date of publication of application:
06.04.88 Bulletin 88/14

(84) Designated Contracting States:
DE FR GB

(88) Date of deferred publication of the search report:
30.08.89 Bulletin 89/35

(71) Applicant: Toho Rayon Co., Ltd.
No. 3-9, Nihonbashi 3-chome
Chuo-ku Tokyo(JP)

(72) Inventor: Kosuda, Hiroyuki Toho Rayon Co.
Ltd.
No. 234, Kamitokari Aza Takaishi
Nagaizumi-cho
Sunto-gun Shizuoka(JP)
Inventor: Nagata, Yasuhisa Toho Rayon Co.
Ltd.
No. 234, Kamitokari Aza Takaishi
Nagaizumi-cho
Sunto-gun Shizuoka(JP)
Inventor: Andoh, Masato Toho Rayon Co. Ltd.
No. 234, Kamitokari Aza Takaishi
Nagaizumi-cho
Sunto-gun Shizuoka(JP)

(74) Representative: Pearce, Anthony Richmond et
al
MARKS & CLERK Alpha Tower Suffolk Street
Queensway Birmingham B1 1TT(GB)

(54) Resin composition of thermosetting resin and thermoplastic resin.

(57) The resin composition which contains thermosetting resin as Component (A), a thermoplastic resin as Component (B), and at least one compound selected from the group consisting of an epoxy resin capable of dissolving the thermoplastic resin and a reactive diluent possessing at least one epoxy group as Component (C) in a ratio such that the proportions of Components (A), (B), and (C) fall respectively in the ranges of 30 to 96% by weight, 2 to 50% by weight, and 2 to 49% by weight, based on the total weight of the resin composition. The resin composition is capable of producing a molded article combining the highly satisfactory mechanical and thermal properties of a thermosetting resin and the highly satisfactory toughness of a thermoplastic resin.

in.

EP 0 262 891 A3



EP 87 30 8550

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl.4)
Y	DE-A-3 009 687 (SIEMENS) * Claims; page 4, lines 25-36 * ---	1-23	C 08 L 63/00 // C 08 J 3/00
Y	PATENT ABSTRACTS OF JAPAN, vol. 6, no. 90 (C-104)[968], 27th May 1982; & JP-A-57 21 428 (TOHO BESLON K.K.) 04-02-1982 * Claims * -----	1-23	(C 08 L 63/00 C 08 L 101:00)
			TECHNICAL FIELDS SEARCHED (Int. Cl.4)
			C 08 J C 08 L
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 14-06-1989	Examiner DERAEDT G.
CATEGORY OF CITED DOCUMENTS			
<p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

12

EUROPEAN PATENT APPLICATION

21 Application number: 87308550.0

51 Int. Cl.⁴: **C 08 L 63/00**

// C08J3/00, (C08L63/00, 101:00)

22 Date of filing: 28.09.87

30 Priority: 30.09.86 JP 232964/86
11.03.87 JP 54180/87
11.03.87 JP 54181/87

43 Date of publication of application:
06.04.88 Bulletin 88/14

84 Designated Contracting States: DE FR GB

71 Applicant: Toho Rayon Co., Ltd.
No. 3-9, Nihonbashi 3-chome
Chuo-ku Tokyo (JP)

72 Inventor: Kosuda, Hiroyuki Toho Rayon Co. Ltd.
No. 234, Kamitokari Aza Takaiishi Nagaizumi-cho
Sunto-gun Shizuoka (JP)

Nagata, Yasuhisa Toho Rayon Co. Ltd.
No. 234, Kamitokari Aza Takaiishi Nagaizumi-cho
Sunto-gun Shizuoka (JP)

Andoh, Masato Toho Rayon Co. Ltd.
No. 234, Kamitokari Aza Takaiishi Nagaizumi-cho
Sunto-gun Shizuoka (JP)

74 Representative: Pearce, Anthony Richmond et al
MARKS & CLERK Alpha Tower Suffolk Street
Queensway Birmingham B1 1TT (GB)

54 Resin composition of thermosetting resin and thermoplastic resin.

57 The resin composition which contains thermosetting resin as Component (A), a thermoplastic resin as Component (B), and at least one compound selected from the group consisting of an epoxy resin capable of dissolving the thermoplastic resin and a reactive diluent possessing at least one epoxy group as Component (C) in a ratio such that the proportions of Components (A), (B), and (C) fall respectively in the ranges of 30 to 96% by weight, 2 to 50% by weight, and 2 to 49% by weight, based on the total weight of the resin composition. The resin composition is capable of producing a molded article combining the highly satisfactory mechanical and thermal properties of a thermosetting resin and the highly satisfactory toughness of a thermoplastic resin.

Description

RESIN COMPOSITION OF THERMOSETTING RESIN AND THERMOPLASTIC RESIN

FIELD OF THE INVENTION

5 This invention relates to a resin composition which uniformly contains a thermosetting resin and a thermoplastic resin and permits production of a shaped article combining highly desirable mechanical and thermal properties of the thermosetting resin and highly desirable toughness of the thermoplastic resin.

BACKGROUND OF THE INVENTION

10 In recent years, shaped articles of thermosetting resin and composite materials using matrices of thermosetting resin have been finding extensive applications in the general industrial field and the electric field because they exhibit highly desirable dimensional stability, heat resistance, mechanical properties, chemical resistance, and weather proofing properties.

15 Such molded articles of thermosetting resins have low toughness and impact resistance due to the low elongation and brittleness of the resin. Thus, improvement in these properties have been desired.

In order to improve the toughness and impact resistance of molded articles of thermosetting resins, a rubber component, plastic resin component or a filler have been incorporated into the thermosetting resins.

20 In the case of incorporation of the rubber component into the thermosetting resin, however, since the rubber component impairs the heat resistance and mechanical properties of the molded article in spite of its ability to improve the toughness and impact resistance of the molded article, the amount of the rubber component is limited. In some applications, it is incorporated into the thermosetting resin only in a low ratio and consequently has an insufficient effect in improving the desired properties. When the thermosetting resin is mixed with a thermoplastic resin, the thermoplastic resin is added to the thermosetting resin as fine powder, or the thermoplastic resin is dissolved in a solvent and subsequently the thermosetting resin is added to the resultant solution (mixture). When the thermoplastic resin is added to a thermosetting resin in a finely divided form, the produced composition lacks homogeneity, and tends to degrade the mechanical properties of the molded article obtained therefrom. When the mixing is effected with the aid of a solvent, the method has the disadvantage that the removal of the solvent from the produced composition is required; the procedure for the production of the composition is troublesome; and the solvent remaining in the produced composition in a minute amount impairs, for example, the heat resistance of the molded article.

SUMMARY OF THE INVENTION

35 An object of the invention is to provide a resin composition which is free from the disadvantages mentioned above and which is produced homogeneously and easily by mixing a thermosetting resin and a thermoplastic resin in the absence of a solvent.

A further object of the invention is a resin composition that permits production of a molded article excelling in heat resistance and in mechanical properties such as toughness and impact resistance.

Additional objects and characteristics of the present invention will become apparent from the following disclosure of the invention.

40 It has now been found that these and other objects of the invention can be attained by the resin composition which contains thermosetting resin as Component (A), a thermoplastic resin as Component (B), and at least one compound selected from the group consisting of an epoxy resin capable of dissolving the thermoplastic resin and a reactive diluent possessing at least one epoxy group as Component (C) in a ratio such that the proportions of Components (A), (B), and (C) fall respectively in the ranges of 30 to 96% by weight, 2 to 50% by weight, and 2 to 49% by weight, based on the total weight of the resin composition.

DETAILED DESCRIPTION OF THE INVENTION

50 Since during the course of the production of the resin composition, Component (C) dissolves Component (B) and it further functions as a medium between Component (A) and Component (B), the production process is easy to carry out and the thermosetting resin and the thermoplastic resin are homogeneously mixed without the use of a solvent. The molded article obtained from the resin composition, therefore, retains the outstanding mechanical properties inherent in the thermosetting resin component and, at the same time, acquires a notable improvement in toughness and consequently in impact resistance.

55 Examples of Component (A) include an epoxy resin, a phenol resin, an bismaleimide resin, or a polyimide resin.

Examples of an epoxy resin include a bisphenol A type epoxy resin, a urethane modified bisphenol A type epoxy resin, a novolak type epoxy resin, a cresol-novolak type epoxy resin, a glycidyl amine type epoxy resin (such as a tri- or tetra-glycidyl amine type epoxy resin), and an alicyclic type epoxy resin.

Examples for each type of epoxy resins are shown in Table 1 below.

Table 1

<u>Type of epoxy resin</u>	<u>Trade name or code of resin</u>	<u>Manufacturer of epoxy resin</u>
Glycidyl amine	Araldite MY 720	Ciba Geigy
	Epototo YH 434	Toto Kasei Co.
	" YDM 120	"
Phenol novolak	Epikote 152	Shell Chemical Co.
	" 154	"
	Dow Epoxy DEN 431	Dow Chemical Co.
	" 438	"
	" 439	"
	EPPN 201	Nippon Kayaku Co.
	Epiclon N 240	Dainippon Ink Chemicals Co.
Cresol novolak	EPN 1138	Ciba Geigy
	Araldite ECN 1235	Ciba Geigy
	" ECN 1273	"
	" ECN 1280	"
	EOCN 102	Nippon Kayaku Co.
	" 103	"
	" 104	"
Bisphenol A	Epikote 815	Shell Chemical Co.
	" 828	"
	" 834	"
Bisphenol A	Epikote 1001	Shell Chemical Co.
	" 1002	"
Urethane modified Bisphenol A	Adeka Resin EPU-6	Asahi Denka Co.
	" EPU-10	"
	" EPU-15	"
Alicyclic	Araldite CY-179	Ciba Geigy Co.
	" CY-178	"
	" CY-182	"
	" CY-183	"

One resin or a mixture of two or more resins described above may be used.

Examples of a phenol resin include a resorcinyl type phenol resin (typified by the product of Showa Union Gosei Co., Ltd., marketed under the product code "BLS-3135") and a novolak type phenol resin (typified by the product of Mitsui-Toatsu Chemical Inc., marketed under the product code "XL-210A" and "XL-225").

5 The commercially available bismaleimide resins include, for example, the product of Mitsubishi Gas Chemical Ltd. marketed under the trademark designation of "BT Resin" such as "BT-2160L", "BT-2160", "BT-2164" and "BT-2170" (these resins are reaction products of 2,2-bis(cyanatophenyl)propane and bis(4-maleimidophenyl)methane) and the product of Boots Technochemie marketed under the trademark designation of "Compimide" such as "Compimide H-800."

10 Examples of the polyimide resin include products developed by NASA and marketed under the product codes of "PMR-15" and "LARC-160" and the product of E.I. Du Pont Co., marketed under the product code of "NR-150."

As the thermosetting resin component (A), it is possible to use in combination two or more different resins selected from the same type or different types, such as, for example, the combination of an epoxy resin and a bismaleimide resin, to suit the particular application.

15 In the present invention, the thermoplastic resin as Component (B) includes, for example, a polycarbonate, a polyether ketone, a polysulfone, a polyether sulfone, a polyether imide, or an aromatic polyester. In the examples cited above, the polycarbonate, polyester, polyether sulfone, polyether imide, and aromatic polyester are preferred since they are easily dissolved in Component (C) to form a homogeneous mixture. Optionally, two or more such thermoplastic resins may be used in combination.

20 The thermoplastic resin as Component (B) is preferably used in the form of particles having diameters of not more than about 400 μm , preferably not more than about 100 μm . Further, it preferably has a glass transition temperature of not less than about 100°C, from the standpoint of heat resistance.

25 As Component (C) used in the present invention, the epoxy resin possessing an ability to dissolve a thermoplastic resin includes a glycidyl-ester type epoxy resin (typified by the product of Shell Chemical Co. marketed under the trademark designation of "Epikote 191").

30 A reactive diluent which is conventionally used in an epoxy resin and which possesses the ability to dissolve the thermoplastic resin used as Component (B) can also be used as Component (C), including a diepoxy compound or a monoepoxy compound. Examples of the diepoxy compound include diglycidyl aniline, diglycidyl toluidine, diglycidyl ether, butane diol glycidyl ether, 2-glycidyl phenyl glycidyl ether, and resorcinol diglycidyl ether. Examples of the monoepoxy compound include alkylphenol glycidyl ether, phenyl glycidyl ether, butyl glycidyl ether, cresol glycidyl ether, glycidyl aniline glycidyl toluidine and styrene oxide.

Optionally, two or more such epoxy resins and/or reactive diluents may be used in combination. The epoxy resin and/or reactive diluent to be used preferably has a viscosity of not more than about 150 poises at 25°C.


35 Generally, Component (B) and Component (C) are appropriately selected such that the latter component is able to dissolve the former component at a lower temperature than the curing temperature of the resin composition. If this relationship is not satisfied, the resin composition produced will lack the homogeneity required, and the advantages of this invention will not be attained.

40 Example of preferred combinations of Component (B) and Component (C) are as follows.

Table 2

Component (B)	Component (C)	
PES	GAN, GOT, PGE, GE, HGE, PPG	5
PEI	GAN, GOT, PGE, HGE, PPG	
PSu	GAN, GOT, PGE, BGE, HGE, PPG	10
PC	GOT, PGE, BGE, HGE	
(Note)	PES: Polyether sulfone (e.g., VICTREX: product of Imperial Chemical Industries Co.)	15
	PEI: Polyether imide (e.g., ULTEM: product of General Electric Plastics)	20
	PSu: Polysulfon (e.g., Udel: product of Union Carbide Co.)	
	Pc: Polycarbonate (e.g., Panlite: product of Teijin Kasei Co.)	25
	GAN: Glycidyl aniline	
	GOT: Glycidyl toluidine	30
	PGE: Phenyl glycidyl ether	
	BGE: Butyl glycidyl ether	35
	GE: Glycidyl ester type epoxy resin (e.g., Epikote 191: product of Shell Chemical Co.)	40
	HGE: Hexanediol diglycidyl ether	
	PPG: Polypropylene glycol diglycidyl ether	45


It is preferred to use a bismaleimide resin comprising a bismaleimide and a biscyanic acid ester, as Component (A). The bismaleimide is preferably a compound represented by the following formula (1) or a prepolymer derived from the compound alone or derived by addition reaction of a compound such as amine to the compound:



wherein R_1 represents a divalent aromatic or aliphatic group, and X_1 and X_2 , which may be the same or different, each represents a hydrogen atom, a halogen atom or an alkyl group. Examples for each aromatic and aliphatic group includes, diphenylene ether and diphenylene methane. Examples for each halogen atom and alkyl group includes chlorine atom and methyl, respectively. The prepolymer is obtained by a heat-reaction of a bismaleimide under the presence of a catalyst, if desired. The reaction may be conducted under the presence

of a compound having at least one amino group, such as triethylene diamine and 2-methyl imidazole. The reaction is conducted until the viscosity of the reaction product becomes from 10 to 1000 poise at 25°C.

The biscyanic acid ester is preferably selected from the group consisting of a cyanic acid ester represented by the following formula (2) and a prepolymer derived from the cyanic acid ester.



wherein R_2 represents a divalent aromatic group, n is an integer of from 2 to 10, and $-\text{O}-\text{C}=\text{N}$ bonds directly to the aromatic ring group represented by R_2 . Examples for R_2 include diphenylene propane.

Component (A) containing the bismaleimide resin further may contain an epoxy resin, preferably in an amount of from about 5 to 50 weight% based on the total weight of Component (A).

In the combination of Component (A)/Component (B)/Component (C), for the purpose of simplifying the procedure for providing the resin composition, it is desirable to dissolve Component (B) initially in Component (C) and subsequently to add Component (A) to the resulting solution. These three components may be mixed simultaneously.

The mixing ratio of Component (A)/Component (B)/Component (C) is such that the proportions of Components (A), (B), and (C) will respectively fall in the ranges of about 30 to 96% by weight, about 2 to 50% by weight, and about 2 to 49% by weight, based on the total weight of Components (A), (B) and (C).

If the proportion of Component (A) falls outside the specified range, the object of this invention cannot be attained. If the proportion of Component (B) exceeds about 50% by weight, the produced resin composition possesses high melt viscosity making the mixing of the components, the impregnation of fibers with the mixed components, and the forming of the mixed components into a molded article difficult, rendering the production of a highly desirable molded article impracticable. If the proportion of Component (C) exceeds about 49% by weight, there is the disadvantage that the heat resistance of the molded article is lowered and the mechanical properties thereof are adversely affected. The object of the present invention is not attained when the proportions of Component (B) and Component (C) are each not at least about 2% by weight. The weight ratio of Component (B)/Component (C) is preferably not more than about 2. If this ratio exceeds about 2, the produced composition possesses a viscosity so high as to make its handling difficult and, when it is used as a prepreg, entails a disadvantage that its ability to impregnate fibers is lowered and its tackiness is insufficient. Moreover, the molded article obtained from the composition has inferior mechanical properties. The necessary amount of Component (C) is determined depending on the amount of Component (B), and it is preferably restricted to the smallest allowable level at which the produced resin composition has the desired homogeneity. The amount of Component (B) and Component (C) is preferably from about 10 to 30% by weight and about 5 to 30% by weight, respectively, based on the total weight of Components (A), (B) and (C).

The resin composition of the present invention, depending on the purpose, the use, and the conditions of use, may have incorporated therein a reinforcing material such as reinforcing fibers, for example, glass fibers, carbon fibers, aromatic polyamide fibers, or metal fibers in addition to the essential components thereof mentioned above. A mixture of these two or more type of fibers may be used.

The reinforcing fibers preferably have a tensile strain of at least about 1.3%. Usually glass fibers and aromatic fibers have a tensile strain of at least about 2.5%. When carbon fibers having a tensile strain of less than about 1.3% are used, a cured composite having insufficient impact resistance is obtained. In order to obtain a composite having a high mechanical properties, it is preferable to use carbon fibers having a tensile strength of at least about 400 kgf/mm² and a tensile modulus of elasticity of at least about 30,000 kg/mm². The reinforcing fibers usually are used up to about 70 volume% based on the total volume of the resin composition (including fibers).

It may further optionally have incorporated therein, for example, a material which increases the toughness of the molded articles, such as butadiene-acrylonitrile rubber, a flame-retardant such as antimony trioxide, a filler such as powdered silica, a coloring agent. These additive materials are incorporated in the composition in an amount up to about 5% by weight based on the weight of the total weight of the composition (including the additive materials).

Some of the resins used in this invention require use of a cross-linking reaction initiator, a curing agent, and a curing accelerator and others are of a kind not requiring these agents. Thus, these resins may be suitably selected as occasion demands.

As a cross-linking reaction initiator, a curing agent, and a curing accelerator, materials which are conventionally used for such purposes can be used in the present invention. A curing agent for an epoxy resin and a curing accelerator for other thermosetting resins are typically used in amounts of from about 25 to 45% by weight and 0 to about 3% by weight, respectively, based on the total weight of thermosetting resin in the composition.

Examples of a cross-linking reaction initiator include an amine, a peroxide, and an organic metal complex.

Examples of a curing agent for an epoxy resin include an aromatic amine such as m-phenylene diamine, diaminodiphenyl methane, diaminodiphenyl sulfone, and m-xylene diamine; a boron trifluoride complex such as BF₃ monoethylamine and BF₃ benzylamine; an acid anhydride such as phthalic acid anhydride, trimellitic acid anhydride, pyromellitic acid anhydride, and benzophenone, tetracarboxylic acid anhydride; an imidazole such as 2-ethyl-4-methylimidazole, 2-ethylimidazole, 2,4-dimethylimidazole, and 2-phenylimidazole, dicyandiamide, and a dibasic acid dihydrazide. Two or more curing agent may be used in combination.

Examples of a curing accelerator include a urea compound such as 3-(3,4-dichlorophenyl)-1,1-dimethyl urea, an organic metal salt such as Co(III) or Fe(III)acetylacetonate, a peroxide such as dicumyl peroxide, and an imidazole compound such as 2-ethyl-4-methylimidazole and 2-phenyl-4-methyl-5-hydroxymethylimidazole. A curing accelerator is used in combination with a curing agent.

The resin composition of the present invention can be prepared, for example, by a method described below.

All of the components are supplied to a kneading device and kneaded therein usually under application of heat, desirably in an atmosphere of inert gas. The heating temperature used in this case is lower than the temperature at which the thermosetting resin begins to cure.

Alternatively, for example, Component (B) can be dissolved in Component (C) and subsequently the resultant solution is kneaded with Component (A), when necessary, in combination with a curing agent.

These steps are carried out generally at a temperature in the range of from about 20° to 200°C, preferably at a temperature in the range of from about 50° to 150°C, for 0.5 to 5 hours.

When a prepreg is formed by impregnating reinforcing fibers with the resin composition of the present invention, the impregnation can be carried out by the conventional hot melt method which is disclosed in, for example, U.S. Patent Application Serial No. 761,290.

In the hot melt method a fiber strand or fabric is impregnated with a resin composition, the viscosity of which is decreased by heating to a proper temperature (not higher than the curing temperature of the resin composition) so that impregnation can be conducted. The impregnation is conducted by dipping a fiber strand or fabric into the resin composition, or by placing fiber strands or a fabric in contact with a film of the resin composition and heat-pressing them.

Thus a prepreg having reinforcing fibers therein is produced, and it is used for preparation of a molded article (composite) by curing the resin composition.

For forming the resin composition of the present invention to a molded article, any conventional method can be used including thermal curing, ultraviolet curing, electron beam curing, and curing by the use of water. The appropriate combination of production method and curing method can be easily selected, depending on the particular kind of the thermosetting resin being used in the resin composition.

Since Component (C) dissolves Component (B) and the mixture of Component (C) and Component (B) is miscible with the thermosetting resin Component (A), a homogeneous mixture of the three components is obtained. Moreover, the resin composition does not require a solvent and, therefore, does not have the disadvantageous of a residual solvent. It is a highly satisfactory resin composition combining highly desirable heat resistance due to the thermosetting resin and highly desirable toughness and impact resistance due to the thermoplastic resin.

In some cases Component (B) precipitates in the form of fine particles when the homogeneous mixture of Component (B) and Component (C) is mixed with Component (A). Of course, even in this case, the three components are mixed with much higher homogeneity than when Component (A) and Component (B) are merely mixed with each other.

The resin composition, in the form of either simply molded articles or molded articles made of composite material consisting of the resin composition and reinforcing fibers, will find extensive applications, for example, in the electric field, the medical field, the space and aeronautic field, the civil engineering and construction fields, and the general industrial field.

Now, the present invention will be described more specifically below with reference to working examples and comparative experiments, but the present invention is not to be construed as being limited thereto.

In Examples and Comparative Examples, all parts percents and ratios, including the mixing ratio of materials used in a resin composition, are by weight unless otherwise specified.

In the Examples and Comparative Examples, the glass transition temperature was measured using a differential scattering calorimeter, and fracture toughness was measured by the double cantilever tear test (ASTM D3433-75).

Examples 1-5

Various epoxy resins were used as Component (A). Components (A), (B), and (C), varying in kind and mixing ratio from one combination to another as indicated in Table 2, were weighed out and placed in a beaker. In the beaker, they were stirred and heated at 110°C for one hour to produce a homogeneous mixture of Components (A), (B), and (C).

Then, this mixture and an epoxy resin curing agent such as diaminodiphenyl sulfone added thereto were heated and mixed at 100°C for one hour to produce a thermosetting resin composition. This composition was placed in a silicone rubber mold and cured therein at 180°C for two hours under application of pressure (5 kg/cm²), to obtain a cured article made of the resin composition.

A test piece was cut from the cured article and tested for glass transition temperature, fracture toughness, and Izod impact energy. The results are shown in Table 3 below.

Comparative Examples 1-7

Resin compositions were produced by following the procedure of Examples 1 to 5, except that only Component (A) was used (Comparative Examples 1-5); Component (B) was omitted (Comparative Example 6); and a butadiene-acrylonitrile rubber (product of Ube Industries, Ltd. marketed under trademark designation of "CTBN, Hycar 1300 x 13") was used in the place of Component (B) (Comparative Example 7).

The resin compositions were similarly processed to produce cured articles, which were tested for the same physical properties. The results are shown in Table 3.

From the results, it is clear that the products of Examples 1-5 were superior to those of Comparative Examples 1-7 in terms of fracture toughness, and Izod impact energy. The product of Comparative Example 7 was satisfactory in toughness but was notably deficient in heat resistance.

10

15

20

25

30

35

40

45

50

55

60

65

Table 3

Example No.	Mixing ratio										Property		
	Component (A)		Component (B)		Component (C)		Curing agent		Other		Glass transition temperature (°C)	Fracture toughness (Joule/m ²)	Izod impact energy (Joule/m ²)
	Araldite NY 720	Epikote 828	Poly-ether sulfone	Poly-ether sulfone	Diglycidyl aniline	Phenyl glycidyl ether	Diamino diphenyl sulfone	Dicyan di-ethyl amine	CTBN Hycar 1300x13				
1	40	10	10	20	-	20	-	40	-	-	200	210	30
2	50	-	10	-	20	-	20	40	1.0	0.2	205	180	26
3	30	10	30	-	15	-	-	40	-	0.2	210	120	24
4	60	-	-	10	-	10	10	40	-	-	200	160	28
5	55	10	10	5	10	-	10	40	1.0	-	210	150	24
Comp. Ex. 1	60	20	20	-	-	-	-	50	-	-	215	70	15
" 2	70	-	30	-	-	-	-	50	1.0	0.2	215	65	14
" 3	40	20	40	-	-	-	-	50	-	0.2	215	65	13
" 4	100	-	-	-	-	-	-	50	-	-	220	60	12
" 5	60	20	20	-	-	-	-	50	1.0	-	215	66	13
" 6	60	10	10	-	-	-	20	50	1.0	0.2	210	68	14
" 7	40	10	10	-	-	-	20	40	1.0	0.2	150	180	20

Examples 6-10 and Comparative Examples 8-12

Cured articles were obtained by following the procedures of Examples 1-5, except that a phenol resin or bismaleimide resin shown in Table 4 below was used as Component (A). The resin compositions using the phenol resin were further post-cured by eight hours standing at 220°C. The cured articles were tested for the same properties as mentioned above. The results are shown in Table 4.

From the results, it is evident that the products of Example 6-10 were superior to those of Comparative Examples 8-12 in terms of fracture toughness and Izod impact energy.

10

15

20

25

30

35

40

45

50

55

60

65

Table 4

Example No.	Mixing ratio										Property		
	Component (A)		Component (B)				Component (C)		Curing accelerator		Glass transition temperature (°C)	Fracture toughness (Joule/m ²)	Isod impact energy (Joule/m ²)
	BLSD- 3135	XL- 225	Epikote 828	BT- 2160	Comp- imide H-800	Poly- ether sulfone	Poly- ether imide	Poly- ether sulfone	Digly- cidyl aniline	Cresol glycidyl ether			
6	60	-	-	-	-	10	10	-	20	-	230	-	10
7	-	75	-	-	-	-	15	-	-	10	230	-	8
8	-	-	-	60	-	10	-	10	20	-	205	160	24
9	-	-	10	50	-	20	-	-	-	20	200	180	28
10	-	-	-	-	60	-	-	20	20	-	270	83	18
Comp. Ex. 8	100	-	-	-	-	-	-	-	-	0.3	-	-	4
" 9	-	100	-	-	-	-	-	-	-	-	210	-	3
" 10	-	-	-	100	-	-	-	-	-	-	250	-	10
" 11	-	-	20	60	-	-	-	-	20	-	210	53	12
" 12	-	-	-	-	80	-	-	-	-	0.3	215	60	10
											280	45	

Examples 11-15 and Comparative Examples 13-17

Resin compositions for preregs were obtained by using the materials shown in Table 5 below as Components (A), (B), and (C) in mixing ratios shown in Table 5, to obtain homogeneous mixtures, and by incorporating curing promoters shown in Table 5 in amounts shown in Table 5.

5 Resin films 60 μm thick were obtained from the thus-obtained compositions using a film coater. Carbon fibers ("Besfight IM-500", product of Toho Rayon Co., Ltd.) having a tensile strength of 500 kgf/mm² and a modulus of elasticity of 30,000 kg/mm² were placed on each film and the resin composition was impregnated therein by heating to a temperature of 100°C and pressing at 4 kg/cm² to obtain a unidirectional (direction of fibers) prepreg having a weight of 150 g/m² and containing 34% by weight of the resin.

10 From each prepreg, necessary number of sheets were obtained by cutting, and they were laminated. The laminated product was heat-cured to obtain a molded plate by autoclave molding at 180°C, 4 kg/cm². Test pieces were obtained by cutting the plate, and the glass transition temperature, the interlaminar shear strength (ILSS; measured according to ASTM D2344 with respect to the fiber direction), the compressive strength (measured with respect to the fiber direction according to ASTM D3410), the damaged area resulting from an impact of 340 kgcm/cm and the compressive strength after the impact were measured. The test piece for subjecting the impact test was prepared by laminate 16 prepreg sheets in such a manner that directions of carbon fibers in the preregs become 45°/0°/-45°/90°/90°/-45°/0°/45°/45°/0°/-45°/90°/90°/-45°/0°/45°. The results obtained are shown in Table 5.

20 Comparative Examples 13-17

Comparative test pieces were produced in the same manner as in Examples 11-15 except that Component (B) or Components (B) and (C) were not used. The properties of the comparative test pieces were measured in the same manner as in Examples 11-15, and the results are shown in Table 5.

25 As can be seen in Table 5, there were no remarkable differences between the thermal characteristics of the test pieces of Examples 11-15 and those of the Comparative Examples. However, the damaged areas caused by the impact were much smaller in the test pieces of Examples 11-15 than those of Comparative Examples 13-17, and the compressive strengths after impact were much higher in the samples of Examples 11-15 than those of Comparative Examples 13-17.

30 These results demonstrate that the composites obtained from the composition of the present invention were superior to those of Comparative Examples 13-17 in impact resistance.

Examples 16 and 17

Using the materials and mixing ratios shown in Table 5 below, each Component (B) was mixed with each Component (C) at 110°C for one hour while stirring.

35 Even when Component (B) was used in a high mixing ratio (Example 6), or when Component (C) was used in a small mixing ratio, a homogeneous mixture could be obtained.

To each of the above-described mixtures, each Component (A) and curing accelerator shown in Table 5 were added in the mixing ratio shown in Table 5, and the resultant mixtures were mixed by using a roll mill to obtain resin compositions for preregs. Using these compositions, preregs were obtained in the same manner as in Examples 11-15, and further molded plates were obtained from the preregs in the same manner as in Examples 11-15. The composite properties were measured in the same manner as in Examples 11-15, and the results are shown in Table 5. From the results it can be seen that the composites obtained from the composition of the present invention had excellent impact resistance.

45

50

55

60

65

Table 5

Example No.	Component (A)													Mixing ratio				Component (C)				Curing agent		Other CTBN Hycar 1300x13
	Araldite MY 720	YDM 120	Epikote 828	Epikote 1001	Epikote 152	DEN 485	EPU-6	PES	PER	PSu	GAN	PGE	PPG	Diamino- diphenyl- sulfone	Dicyan diamide	BF ₃ .mono- ethyl- amine	Dichloro- phenyl di- methyl urea							
11	40	-	10	-	10	-	10	15	-	-	15	-	-	35	1.0	0.2	1.0	-						
12	40	10	-	-	10	-	-	-	20	-	-	20	-	30	1.0	0.2	1.0	-						
13	40	-	10	-	20	-	-	10	10	-	20	-	-	30	1.0	0.2	1.0	10						
14	50	-	-	-	10	-	-	-	20	-	-	-	20	33	1.0	0.2	1.0	10						
15	40	10	10	-	10	-	10	-	5	5	10	-	-	38	1.0	0.2	1.0	10						
16	20	-	-	-	20	-	-	40	-	-	-	20	-	20	-	-	-	-						
17	45	-	5	-	10	-	10	10	10	-	10	-	-	30	1.0	0.2	1.0	10						
Comp. Ex. 13	90	-	-	-	-	10	-	-	-	-	-	-	-	45	-	-	-	-						
" 14	50	20	-	15	-	15	-	-	-	-	-	-	-	40	1.0	0.2	1.0	-						
" 15	70	10	-	10	-	8	-	-	1	-	-	1	-	40	1.0	0.2	1.0	10						
" 16	70	-	5	10	10	5	10	-	-	-	10	-	-	40	1.0	0.2	1.0	10						
" 17	60	-	10	15	10	15	-	-	-	-	-	10	-	40	1.0	0.2	1.0	10						

Table 5 (Cont'd)

Example No.	Glass transition temperature (°C)	Property				
		ILSS at 23°C (kgf/mm ²)	ILSS at 82°C (kgf/mm ²)	Compressive strength at 23°C (kgf/mm ²)	Damaged area by impact (cm ²)	Compressive strength after impact (kgf/mm ²)
11	205	11	8.0	140	12	23
12	205	11	8.5	140	10	25
13	200	11	8.0	140	10	24
14	200	11	8.0	140	7	27
15	205	11	8.0	145	15	21
16	200	10	8.0	130	8	27
17	205	10	8.0	140	9	26
Comp. Ex. 13	220	13	10	150	40	12
" 14	215	13	9.0	140	35	12
" 15	210	12	8.5	140	25	14
" 16	205	11	8.5	140	30	13
" 17	205	11	8.5	140	30	13

Examples 18-24 and Comparative Examples 18-22

The same experiments as in Examples 11-17 and Comparative Examples 13-17 were conducted except that materials and mixing ratios shown in Table 6 below were used. The results are shown in Table 6.

From the results it can be seen that the composites obtained from the composition of the present invention had excellent impact resistance.

5

10

15

20

25

30

35

40

45

50

55

60

65

Table 6

Example No.	Mixing ratio													Curing accelerator Co(III) acetyl- peroxide acetate	
	Component (A)					Component (B)		Component (C)		Other CTBN Hycar 1300x13					
	BT- 2160L	BT- 2160	BT- 2164	BT- 2170	Epikote 828	Epikote 1001	Epikote 152	PES	PEI		PSU	GAN	PGE		PPG
18	90	-	-	-	10	-	-	-	15	-	10	-	-	0.1	-
19	80	10	-	-	10	-	-	15	-	-	10	-	-	0.1	0.01
20	80	10	-	-	10	-	-	-	10	10	20	-	-	0.1	-
21	70	-	-	10	-	10	10	-	15	-	-	-	15	0.1	-
22	70	10	10	-	-	-	10	10	10	-	-	10	-	0.1	-
23	80	-	-	-	20	-	-	40	-	-	-	20	-	0.1	0.01
24	70	-	10	-	10	-	10	10	10	-	5	10	-	0.1	-
Comp. Ex. 18	90	-	-	-	10	-	-	-	-	-	-	-	-	0.1	-
" 19	80	10	-	-	10	-	-	-	-	-	-	-	-	0.1	-
" 20	70	10	-	10	-	10	10	-	-	-	-	-	-	0.1	-
" 21	90	-	-	-	10	-	-	-	-	-	10	-	-	0.1	-
" 22	80	10	-	-	10	-	-	-	-	-	-	10	-	0.1	-

Table 6 (Cont'd)

Example No.	Glass transition temperature (°C)	Property				
		ILSS at 23°C (kgf/mm ²)	ILSS at 82°C (kgf/mm ²)	Compressive strength at 23°C (kgf/mm ²)	Damaged area by impact (cm ²)	Compressive strength after impact (kgf/mm ²)
18	215	12	8.0	140	8	27
19	215	12	8.0	140	10	22
20	210	11	7.5	135	10	23
21	215	12	8.0	140	9	25
22	210	11	7.5	135	8	26
23	200	10	7.0	130	6	28
24	210	11	7.5	140	10	21
Comp. Ex. 18	220	13	8.5	150	25	13
" 19	220	13	8.5	140	25	12
" 20	210	12	8.0	140	20	14
" 21	215	11	8.0	140	30	12
" 22	215	11	8.0	140	30	12

While the invention has been described in detail and with reference to specific embodiments thereof, it will be apparent to one skilled in the art that various changes and modifications can be made therein without

departing from the spirit and scope thereof.

5 Claims

1. A resin composition which contains thermosetting resin as Component (A), a thermoplastic resin as Component (B), and at least one compound selected from the group consisting of an epoxy resin capable of dissolving the thermoplastic resin and a reactive diluent possessing at least one epoxy group as Component (C) in a ratio such that the proportions of Components (A), (B), and (C) fall respectively in the ranges of 30 to 96% by weight, 2 to 50% by weight, and 2 to 49% by weight, based on the total weight of the resin composition.

2. The resin composition as in claim 1, wherein said thermosetting resin as Component (A) is a resin selected from the group consisting of an epoxy resin, a phenol resin, a bismaleimide resin, and a polyimide resin.

3. The resin composition as in claim 1, wherein said thermosetting resin as Component (A) is an epoxy resin selected from the group consisting of a bisphenol A type epoxy resin, a urethane modified bisphenol A type epoxy resin, a novolak type epoxy resin, a cresol-novolak type epoxy resin, a glycidyl amine type epoxy resin, and an alicyclic type epoxy resin.

4. The resin composition as in claim 3, wherein said glycidyl amine type epoxy resin is a resin selected from the group consisting of a triglycidyl amine type epoxy resin or a tetraglycidyl amine type epoxy resin.

5. The resin composition as in claim 1, wherein said thermoplastic resin as Component (B) is a resin selected from the group consisting of a polycarbonate, a polyether ketone, a polysulfone, a polyether sulfone, a polyether imide, and an aromatic polyester.

6. The resin composition as in claim 1, wherein said epoxy resin as Component (C) is selected from the group consisting of a glycidyl ester type epoxy resin.

7. The resin composition as in claim 1, wherein said reactive diluent as Component (C) containing at least one epoxy group is selected from the group consisting of diglycidyl aniline, diglycidyl toluidine, diglycidyl ether, butane diol glycidyl ether, 2-glycidyl phenyl glycidyl ether, resorcinyl-diglycidyl ether, alkylphenol glycidyl ether, phenyl glycidyl ether, butyl-glycidyl ether, cresol-glycidyl ether, and styrene oxide.

8. The resin composition as in claim 1, wherein the weight ratio of Component (B) to Component (C) is up to about 2.

9. The resin composition as in claim 1, wherein said thermoplastic resin as Component (B) is a polyether sulfone and said at least one of the epoxy resin and the reactive diluent as Component (C) comprises at least one compound selected from the group consisting of glycidyl aniline, glycidyl toluidine, phenyl glycidyl ether, a glycidyl ester epoxy resin, hexanediol diglycidyl ether and polypropylene glycol diglycidyl ether.

10. The resin composition as in claim 1, wherein said thermoplastic resin as Component (B) is a polyether imide and said at least one of the epoxy resin and the reactive diluent as Component (C) comprises at least one compound selected from the group consisting of glycidyl aniline, glycidyl toluidine, phenyl glycidyl ether, hexanediol diglycidyl ether, and a polypropylene glycol diglycidyl ether.

11. The resin composition as in claim 1, wherein said thermoplastic resin as Component (B) is a polysulfone and said at least one of the epoxy resin and the reactive diluent as Component (C) comprises at least one compound selected from the group consisting of glycidyl aniline, glycidyl toluidine, phenyl glycidyl ether, butyl glycidyl ether, hexanediol diglycidyl ether and a polypropylene glycol diglycidyl ether.

12. The resin composition as in claim 1, wherein said thermoplastic resin as Component (B) is a polycarbonate and said Component (C) comprises at least one compound selected from the group consisting of glycidyl toluidine, phenyl glycidyl ether, butyl glycidyl ether, and hexanediol diglycidyl ether.

13. The resin composition as in claim 1, wherein Components (B) and (C) fall respectively within the ranges of from 10 to 30% by weight and 5 to 30% by weight.

14. The resin composition as in claim 1, further comprising a reinforcing fiber.

15. The resin composition as in claim 14, wherein said fiber is selected from the group consisting of a carbon fiber, a glass fiber and an aromatic polyimide fiber.

16. The resin composition as in claim 14, wherein the amount of said reinforcing fiber is up to about 70% by volume based on the total volume of said composition.

17. The resin composition as in claim 1, further comprising at least one additive selected from butadiene-acrylonitrile rubber, a flame-retardant, a filler, and a coloring agent.

18. The resin composition as in claim 17, wherein the amount of said additive is up to about 5 wt% based on the total weight of said composition.

19. The resin composition as in claim 1, further comprising at least one of a cross-linking reaction initiator, a curing agent, and a curing accelerator.

20. The resin composition as in claim 1, wherein said thermosetting resin as Component (A) comprises a thermosetting resin comprising bismaleimide and a biscyanic acid ester.

21. A method for producing a homogeneous resin which contains thermosetting resin as Component

(A), a thermoplastic resin as Component (B), and at least one compound selected from the group consisting of an epoxy resin capable of dissolving the thermoplastic resin and a reactive diluent possessing at least one epoxy group as Component (C) in a ratio such that the proportions of Components (A), (B), and (C) fall respectively in the ranges of 30 to 96% by weight, 2 to 50% by weight, and 2 to 49% by weight, based on the total weight of the resin composition.

5

22. The method for producing the resin composition as in claim 21, wherein said Component (B) is first dissolved in Component (C), and then the resultant solution is mixed with said Component (A).

23. The method for producing the resin composition as in claim 21, wherein the mixing is conducted at a temperature in the range of from about 20 to 200° C.

10

15

20

25

30

35

40

45

50

55

60

65